

Strong Modul 966

Manufacturing process	Needlefelt							ISO 2424
Type of surface	Flecked							
Surface aspect	Coarse Fibred							ISO 2424
Width	50*50 cm, 25*100 cm							
Backing	BT							ISO 2424
Pile yarn composition	70% doric® PA / 20% PES / 10% PP							ISO 2424
Pile weight	500 g/m²							
Total weight	4200 g/m²				+/- 15%		ISO 8543	
Total height	6,5 mm				+15% / -10%		ISO 1765	
Overall use class	Commercial 33, Areas with heavy use							EN 1307
Luxury class	LC1							EN 1307
Castor chair suitability	Yes, permanent use							EN 985
Colour fastness to light	≥ 5							ISO 105-B02
Colour fastness to rubbing, wet and dry	≥ 4							ISO 105-X12
Colour fastness to water	≥ 4							ISO 105-E01
Electrostatic charging	< 2kV							ISO 6356
Vertical resistance	< 1,0x10 ⁸ Ω							ISO 10965
Impact sound protection ΔLW	20 dB							ISO 10140
Acoustical sound absorption αS	Hz	125	250	500	1000	2000	4000	ISO 354
	αW	0.00	0.03	0.06	0.13	0.30	0.31	
Evaluated sound absorptions grade αW	0.15							ISO 11654
Thermal resistance	0.07 m².K/W							ISO 8302
Slip resistance	> 0,3	Machine direction						EN 13893
	> 0,3	Crossdirection						EN 13893
Flammability	Bfl,s1							EN 13501-1
Prodis-ID (GuT)	AC22A000							www.pro-dis.info
TÜV PROFICERT product	Certificate number: 70 710 5617-4							

Floorsymbols



Certificates



Mitglied der
DGNB
Deutsche Gesellschaft für Nachhaltiges Bauen
German Sustainable Building Council



ISO 9001:2015-certified processes
ISO 14001:2015-certified processes

2019-08-27