


Denim Stonewash

Preliminary specification according to EN 1307



Type of manufacture	ISO 2424	Tufted 1/10 "						
Aspect	ISO 2424	Structured loop pile						
Dye method		Space dyed						
Width		cm	400	ft	13.1			
Primary backing	ISO 2424	Polyester fleece						
Secondary backing	ISO 2424	Felt backing 250g						
Pile fibre composition	ISO 2424	BCF Polyamide 6 ECONYL® (ECONYL® is made from 100% regenerated content) **						
Total thickness	ISO 1765	mm	8.9	inch	0.4			
Effective pile thickness	ISO 1766	mm	3.5	inch	0.14			
Total mass	ISO 8543	g/m ²	2515	oz/yd ²	74.2			
Total pile mass	ISO 2424	g/m ²	850	oz/yd ²	25.1			
Effective pile mass	ISO 8543	g/m ²	420	oz/yd ²	12.4			
Pile density	ISO 8543	g/cm ³	0.119	lb/in ³	0.0043			
Number of tufts	ISO 1763	/dm ²	1378	/yd ²	115215			
Stroll test	ISO 6356	kV	≤ 2,0					
Vertical resistance	ISO 10965	Ohm	-					
Horizontal resistance	ISO 10965	Ohm	-					
Use classification	EN 1307	23 Domestic - heavy use						
Luxury rating	EN 1307	LC 2						
Impact sound reduction ΔL_w	ISO 10140	dB						
Sound absorption	ISO 354	Freq. Hz	125	250	500	1000	2000	4000
		α_s	-	-	-	-	-	-
Noise reduction	ISO 354	α_w	-					
Thermal resistance	ISO 8302	m ² .K/W	-					
Flammability	EN 13501-1	Cfl - s1 (glued tested)						
Prodis - GUT	www.pro-dis.info	5878D92A						



EN 14041
0493-CPR-0003

Manufactured by:

Tarkett BV
Parallelweg 14
NL - 5051 HG Goirle



ENDLESS POSSIBILITIES







Quality- and Environmental
Management System Certification
ISO 9001 & ISO 14001






Tarkett's flooring products are to be installed in full accordance with DESSO installation instructions and recognized trade standards. An effective, regular cleaning and maintenance program is vital for retaining a high appearance level. Tarkett's flooring products should only be used as floorcoverings. Note: Tarkett reserves the right to change this specification without prior notice; changes are subject to normal production tolerances. For the latest versions of the technical specifications, visit www.tarkett.com

EN-20190515