

Strong Compact 926 LV

Manufacturing process	Needlefelt	ISO 2424						
Type of surface	Flecked							
Surface aspect	Coarse Fibred	ISO 2424						
Width	200 cm							
Backing	LV	ISO 2424						
Fibre composition	100% dorix® PA							
Total fibre weight of use surface	500 gr/m ²							
Total weight	1200 gr/m ²	+/- 15% ISO 8543						
Basis weight of pile	450 gr/m ²	+/- 15% EN 984						
Total height	6,0 mm	+15% / -10% ISO 1765						
Overall use class	Commercial 33, Areas with heavy use	EN ISO 10874						
Luxury class	LC1	EN 1307						
Castor chair suitability	Yes, permanent use	EN 985						
Stair suitability	Yes, permanent use	EN 1307						
Colour fastness to light	≥ 5	ISO 105-B02						
Colour fastness to rubbing, wet and dry	≥ 4	ISO 105-X12						
Colour fastness to water	≥ 4	ISO 105-E01						
Dimensional stability	Shrinkage ≤ 1,2 %	ISO 2551						
	Extension ≤ 0,5 %	ISO 2551						
Electrostatic charging	< 2kV	ISO 6356						
Impact sound protection ΔLW	20 dB	ISO 10140						
Acoustical sound absorption α _W	Hz	125	250	500	1000	2000	4000	ISO 354
	α _W	0,00	0,05	0,10	0,20	0,35	0,55	
Evaluated sound absorptions grade α _W	0.20	ISO 11654						
Thermal resistance	0,11 m ² .K/W	ISO 8302						
Slip resistance	DS (> 0,30)	EN 13893						
Flammability	Cfl,s1 (Glued)	EN 13501-1						
Prodis-ID (GuT)	7F55082B	www.pro-dis.info						
TÜV PROFICERT product	Certificate number: 70 710 5617-2							

Floorsymbols



Certificates



ISO 9001:2015-certified processes
 ISO 14001:2015-certified processes

2022-05-02