




Shades

Preliminary specification according to EN 1307

Type of manufacture	ISO 2424	Tufted 1/10 “						
Aspect	ISO 2424	Structured loop pile						
Dye method	Solution dyed							
Width	cm	400	ft	13.1				
Primary backing	ISO 2424	Polyester fleece						
Secondary backing	ISO 2424	Felt backing 250g						
Pile fibre composition	ISO 2424	BCF Polyamide 6						
Total thickness	ISO 1765	mm	7.1	inch	0.3			
Effective pile thickness	ISO 1766	mm	2.9	inch	0.11			
Total mass	ISO 8543	g/m ²	2015	oz/yd ²	59.5			
Total pile mass	ISO 2424	g/m ²	520	oz/yd ²	15.3			
Effective pile mass	ISO 8543	g/m ²	315	oz/yd ²	9.3			
Pile density	ISO 8543	g/cm ³	0.108	lb/in ³	0.0039			
Number of tufts	ISO 1763	/dm ²	2157	/yd ²	180347			
Stroll test	ISO 6356	kV	≤ 2,1					
Vertical resistance	ISO 10965	Ohm	-					
Horizontal resistance	ISO 10965	Ohm	-					
Use classification	EN 1307	23 Domestic - heavy use						
Luxury rating	EN 1307	LC 1						
Impact sound reduction ΔL _w	ISO 10140	dB	30					
Sound absorption	ISO 354	Freq. Hz	125	250	500	1000	2000	4000
		α _s	0.02	0.00	0.17	0.46	0.55	0.55
Noise reduction	ISO 354	α _w	0.25					
Thermal resistance	ISO 8302	m ² .K/W	0.115					
Flammability	EN 13501-1	Cfl - s1 (glued tested)						
Prodis - GUT	www.pro-dis.info	E1D00797						


Manufactured by:
Tarkett BV
Parallelweg 14
NL - 5051 HG Goirle

EN 14041
0493-CPR-0003























Tarkett's flooring products are to be installed in full accordance with DESSO installation instructions and recognized trade standards. An effective, regular cleaning and maintenance program is vital for retaining a high appearance level. Tarkett's flooring products should only be used as floorcoverings. Note: Tarkett reserves the right to change this specification without prior notice; changes are subject to normal production tolerances. For the latest versions of the technical specifications, visit www.tarkett.com

EN-20190516